

Description

FEDERATED 20W50 12/1QT

Inspection Information	Test Method	Typical Value
Gravity, °API	ASTM D287	29.59
Specific Gravity at 60°F (15.6°C)	ASTM D4052	0.8784
Flash Point, °C	ASTM D92	240
Flash Point, °F	ASTM D92	464
Viscosity at 40°C, cSt	ASTM D445	161.6
Viscosity at 100°C, cSt	ASTM D445	17.45
Viscosity Index	ASTM D2270	118
Pour Point, °C (°F)	ASTM D5950	-30°C (-22°F)
Cold Cranking Simulator at (°C), cP	ASTM D5293	8341 (-15)
High Temperature / High Shear Vis at 150°C, cP	ASTM D5481	4.58
Noack Volatility, % loss	ASTM D5800	4.6
Color	ASTM D1500	2.5
Zinc, wt. %	ASTM D5185	0.07
Phosphorus, wt. %	ASTM D5185	0.064
Calcium, wt. %	ASTM D5185	0.119
Sulfur, wt. %	ASTM D4951	0.235
Magnesium, wt. %	ASTM D5185	0.038
Boron, wt. %	ASTM D5185	0.007
Molybdenum, wt. %	ASTM D5185	0.004
Sulfated Ash, wt. %	ASTM D874	0.712
Nitrogen, wt. %	ASTM D4629	0.081
Pumping Viscosity at (°C), cP	ASTM D4684	22,900 (-20)
Shear Stability, Final Viscosity in cSt	ASTM D6278	15.4
Foam Seq. I (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. II (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. III (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
High Temperature Foaming, static foam	ASTM D6082 (Opt A)	10/0
TBN, mgKOH/g	ASTM D2896	7

Claims Information

API SJ, SH, SG, SF, SE, SD, SC	Recommended For
API SL	Recommended For
API SM	Recommended For
API SN	Recommended For
API SN PLUS	Recommended For
API SP	Approved