

Description

FEDERATED HD 40 12/1QT

Inspection Information	Test Method	Typical Value
Gravity, °API	ASTM D287	28.88
Specific Gravity at 60°F (15.6°C)	ASTM D4052	0.8823
Flash Point, °C	ASTM D92	230
Flash Point, °F	ASTM D92	446
Viscosity at 40°C, cSt	ASTM D445	123
Viscosity at 100°C, cSt	ASTM D445	13.26
Viscosity Index	ASTM D2270	102
Pour Point, °C (°F)	ASTM D5950	-30°C (-22°F)
High Temperature / High Shear Vis at 150°C, cP	ASTM D5481	3.89
Noack Volatility, % loss	ASTM D5800	3.4
Color	ASTM D1500	2.5
Zinc, wt. %	ASTM D5185	0.07
Phosphorus, wt. %	ASTM D5185	0.064
Calcium, wt. %	ASTM D5185	0.119
Sulfur, wt. %	ASTM D4951	0.235
Magnesium, wt. %	ASTM D5185	0.038
Boron, wt. %	ASTM D5185	0.007
Molybdenum, wt. %	ASTM D5185	0.004
Sulfated Ash, wt. %	ASTM D874	0.712
Nitrogen, wt. %	ASTM D4629	0.081
Foam Seq. I (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. II (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
Foam Seq. III (Tendency/Stability), mL	ASTM D892 (Opt. A)	0/0
High Temperature Foaming, static foam	ASTM D6082 (Opt A)	10/0
TBN, mgKOH/g	ASTM D2896	7

Claims Information

API SJ, SH, SG, SF, SE, SD, SC	Recommended For
API SL	Recommended For
API SM	Recommended For
API SN	Recommended For
API SN PLUS	Recommended For
API SP	Approved